

# Product sheet **GR**

## **noxifer**<sup>®</sup>

**NOXIFER S.L.**

Ctra de Sarral a Barberà, parcel·la 21  
43424 - SARRAL (Tarragona) - España

### **ESSENTIAL FEATURES**

Weldability	NPD
Breaking strenght	195 Mpa at 23°C, 5mm/min according to ISO527-1/2
Maximum continuous use temperature	110°C - 20000 h 50% tension resistance IEC 216
Cadmium emission	NO EMISSIONS
Radioactivity emission	NO EMISSIONS
Durability	NPD

### **STRUCTURAL FEATURES**

Base material	Badamid® B70 GF30 FR HF
Fusion temperature	222°C - 10 K/min according to ISO 3146
Fatigue resistance	NPD (Static loads)
Bearing capacity	Characteristic values of actions

